## NOTES:

SUBSTRATE:

GRADE A FINE ANNEALED SCHOTT: N-BK7 517/642

2. ROHS COMPLIANT

3. CENTERING TOLERANCE (AT 587.6nm): BEAM DEVIATION (HALF ANGLE): <1 ARCMIN

4. COATING (APPLY ACROSS COATING APERTURE)

\$1 & \$2: YAG-BBAR R(AB\$) < 0.25% @ 532nm @ 0° AOI R(AB\$) < 0.25% @ 1064nm @ 0° AOI R(AVG) < 1.0% FROM 500-1100nm @ 0° AOI

5. FINE GRIND SURFACE


6. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE


7. FOCAL LENGTH (EFL): 200.00mm±1% BACK FOCAL LENGTH (BFL): 197.35mm

8. PROTECTIVE BEVEL AS NEEDED

9. DESIGN WAVELENGTH: 587.6nm

10. BLACKENED SURFACE





**SECTION A-A** 

## FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

|                         | \$1        | \$2        |  |  |  |  |
|-------------------------|------------|------------|--|--|--|--|
| SHAPE                   | CONVEX     | CONVEX     |  |  |  |  |
| RADIUS                  | 205.35     | 205.35     |  |  |  |  |
| SURFACE QUALITY         | 40 - 20    | 40 - 20    |  |  |  |  |
| MIN CLEAR APERTURE      | Ø39.00     | Ø39.00     |  |  |  |  |
| MIN COATING APERTURE    | Ø39.00     | Ø39.00     |  |  |  |  |
| POWER AT 632.8nm        | 3.00 RINGS | 3.00 RINGS |  |  |  |  |
| IRREGULARITY AT 632.8nm | 0.50 RINGS | 0.50 RINGS |  |  |  |  |

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

|                        |    | <b>Edmund Optics</b> ® |   |                 |
|------------------------|----|------------------------|---|-----------------|
| THIRD ANG<br>PROJECTIO |    | TITLE                  | 40mm Dia. x 200mm FL, YAG-BBAR<br>Coated, Inked, Double-Convex Lens |                 |
| ALL DIMS IN            | mm | DWG NO                 | 34198INK  | SHEET<br>1 OF 1 |