NOTES:

- SUBSTRATE
- 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN 5 arcsec
- 3. COATING (APPLY ACROSS COATING APERTURE)

ENVIRONMENTAL DURABILITY:

PHYSICAL DURABILITY:

PERFORMANCE SPECIFICATIONS:

T(avg): >85% FROM 624 - 1152nm FOR RANDOM POLARIZATION @ 45° AOI T(abs): >80% FROM 624 - 1152nm FOR ALL POLARIZATIONS @ 45° AOI R(avg): >97% FROM 1260 - 1560nm FOR RANDOM POLARIZATION @ 45° AOI R(abs): >95% FROM 1260 - 1560nm FOR ALL POLARIZATIONS @ 45° AOI

S1

PLANO

60-40


11.0 x 16.0

T(abs): = 50% 1200nm @ 45° AOI

\$1: HARD COATED S2: SINGLE LAYER MgF2

4. FINE GRIND SURFACE

- 5. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 6. TRANSMITTED WAVEFRONT DISTORTION RMS@ 632.8nm ≤ ¼ λ
- 7. ROHS COMPLIANT




SHORTPASS FILTER

SHAPE

BEVEL

SURFACE QUALITY

CLEAR APERTURE



PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

S2 PLANO THIRD 60-40 PROJE 11.0 x 16.0 ALL D PROTECTIVE AS NEEDED PROTECTIVE AS NEEDED



DANGLE TITLE		TITLE	12.5 x 17.6mm, 1200nm DICHROIC SHORTPASS FILTER	
DIMS IN	mm	DWG NO	86687	SHEET 1 OF 1

