NOTES:

1. SUBSTRATE: FUSED SILICA

2. COATING (APPLY ACROSS COATING APERTURE):

LASER NIR (1030-1550nm) R(AVG) ≤0.7% @ 1030 - 1550nm @ 0° AOI

DAMAGE THRESHOLD, PULSED: 2 J/cm² @ 1064nm, 20ns, 20Hz

- 3. TRANSMITTED WAVEFRONT DISTORTION P-V: $\lambda/10$ for 1.1mm input beam (nominal, λ = DWL)
- 4. ROHS COMPLIANT

