NOTES:

- SUBSTRATE
- 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN 5 arcsec
- 3. COATING (APPLY ACROSS COATING APERTURE) PERFORMANCE SPECIFICATIONS:

T(avg): >85% FROM 400 - 775nm FOR RANDOM POLARIZATION @ 45° AOI T(abs): >80% FROM 400 - 775nm FOR ALL POLARIZATIONS @ 45° AOI R(avg): >97% FROM 850 - 1050nm FOR RANDOM POLARIZATION @ 45° AOI

R(abs): >95% FROM 850 - 1050nm FOR ALL POLARIZATIONS @ 45° AOI


T(abs): = 50% 800nm @ 45° AOI

GDD: 80 ± 30fs² @ 510 - 775nm 120 ± 80fs² @ 400 - 775nm

\$1: HARD COATED \$2: SINGLE LAYER MgF2

4. FINE GRIND SURFACE


- POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 6. TRANSMITTED WAVEFRONT DISTORTION RMS@ 632.8nm ≤ ¼ λ
- 7. ROHS COMPLIANT



SHORTPASS FILTER

25.20 _{-0.10}	_
	25 (0.000
	35.60 0.00

PARTS TO THIS DRAWING



SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2
SHAPE	PLANO	PLANO
SURFACE QUALITY	40-20	40-20
CLEAR APERTURE	24.2 x 34.6	24.2 x 34.6
COATING APERTURE	24.2 x 34.6	24.2 x 34.6
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED

			Edmund Optic	S®
THIRD ANGLE PROJECTION		TITLE	800nm, 25.2 x 35.6mm, Low GDD Dich Shortpass Ultrafast Filter	nroic
ALL DIMS IN	mm	DWG NO	14015	SHEET 1 OF 1