NOTES:

- SUBSTRATE
- 2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN 5 arcsec
- 3. COATING (APPLY ACROSS COATING APERTURE) PERFORMANCE SPECIFICATIONS:

T(avg): >85% FROM 400 - 820nm FOR RANDOM POLARIZATION @ 45° AOI T(abs): >80% FROM 400 - 820nm FOR ALL POLARIZATIONS @ 45° AOI

R(avg): >97% FROM 910 - 1110nm FOR RANDOM POLARIZATION @ 45° AOI R(abs): >95% FROM 910 - 1110nm FOR ALL POLARIZATIONS @ 45° AOI


T(abs): = 50% 850nm @ 45° AOI

GDD: 80 ± 30fs² @ 440 - 820nm 120 ± 80fs² @ 410 - 820nm

\$1: HARD COATED \$2: SINGLE LAYER MgF2

4. FINE GRIND SURFACE


- POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 6. TRANSMITTED WAVEFRONT DISTORTION RMS@ 632.8nm ≤ ¼ λ
- 7. ROHS COMPLIANT



SHORTPASS FILTER

25.20 -0.3	20	
		<u> </u>
		35.60 0.00
		00.00 -0.20

PARTS TO THIS DRAWING



SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2
SHAPE	PLANO	PLANO
SURFACE QUALITY	40-20	40-20
CLEAR APERTURE	24.2 x 34.6	24.2 x 34.6
COATING APERTURE	24.2 x 34.6	24.2 x 34.6
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED

				Edmund Optics®			
	THIRD ANGLE PROJECTION	$\phi \Leftrightarrow$	TITLE	850nm, 25.2 x 35.6mm, Low GDD Dichroic Shortpass Ultrafast Filter			
I	ALL DIMS IN	mm	DWG NO	14016	SHEET 1 OF 1		